


The electron-phonon interaction in ABINIT



Overview

- General introduction
- Formalism
- Implementation
 - Datastructures
 - Subroutines
- Present status

General Introduction

- El – phon interaction enters in
 - Resistivity
 - Superconductivity
 - Spectroscopies (Raman...)
- BO – approximation
- Independent quasiparticles, then coupled
(see van Leeuwen PRB 69 115110
and EKV Gross' group's publications
Savrasov...)

Formalism

Allen & Mitrovic Sol Stat Phys 37

- Naïve approach

$$\hat{H} = \hat{H}_{el} + \hat{H}_{ph} + \hat{H}_{e-ph}$$

- In ABINIT phonons from BO linear response
- Hence partially pre-screened, but it works and everybody else does it so why can't we?
- Lowest order (Migdal): 1 phonon scattering for 1 quasi-electron

Formalism II

- el-ph self energy

$$\Sigma_{ep} = T \int_{FS} \int_{\Omega} \frac{\alpha^2 F(k, k', \Omega)}{N(0)} \left(\frac{2\Omega}{\omega^2 + \Omega^2} \right) G$$

$$\alpha^2 F(k, k', \Omega) = N(0) \sum_j |g_{k, k'}^j|^2 \delta(\omega_{q, j} - \Omega)$$

- Eliashberg function
- gkk matrix elements

Formalism III

$$g_{k,k'}^j = \frac{1}{\sqrt{2 M \omega_{q,j}}} \epsilon_{q,j} \cdot \langle k | \nabla V | k' \rangle$$

- From linear response we have
 - The matrix elements
 - The phonon frequencies & eigenvectors

Formalism IV

- Mass enhancement parameter λ is 1st inv moment

$$\lambda(k, k', \omega) = \int_0^\infty d\Omega \frac{2\Omega}{\omega^2 + \Omega^2} \alpha^2 F(k, k', \Omega)$$

- Phonon line widths:

$$\gamma_{q,j} = 2\pi \omega_{q,j} \int_{FS} |g_{k+q,k}^{qj}|^2$$

Formalism V

- McMillan isotropic T_c formula:

$$T_c = \frac{\omega_{\log}}{1.2} \exp\left(\frac{-1.04(1+\lambda)}{\lambda - \mu^*(1+0.62\lambda)}\right)$$

- log average frequency:

$$\omega_{\log} = \exp\left(\frac{2}{\lambda} \int_0^{\infty} d\Omega \alpha^2 F(\Omega) \frac{\ln(\Omega)}{\Omega}\right)$$

Formalism VI

- Eliashberg anisotropic equations:

$$Z(k, n) = 1 + \frac{\pi T}{|\omega_n| N(0)} \sum_{k' \in FS, n'} \lambda(k, k'; n - n') s_n s_{n'}$$

$$Z(k, n) \Delta(k, n) = \pi T \sum_{k' \in FS, n'} \frac{1}{N(0) |\omega_{n'}|} [\lambda(k, k'; n - n') - \mu^*] \Delta(k', n')$$

- Solve for T_c such that largest eigenvalue of kernel is 1
- Linearize equations around isotropic solution, or
- Brute force...

Implementation


- Post-processing job in anadddb
 - Phonon runs for all modes and minimal qpoints,
 - mrggkk: Extract matrix elements which are by-product in 1WF files
 - Then 3 steps in data processing:
 - $|gkk|^2$ matrix elements in recip space
 - FT in real space
 - $|gkk|^2$ on dense kpoint grid used for respfn

Implementation II

- Characterize Fermi surface (gaussian smearing gives weighted sum over kpts)
- New elph_type datatype for $|g_{kk}|^2$ and dims, files ...
- And, optionally, keep large matrices on disk

- Calculate linewidths
- Calculate α^2F , ω_{\log} , McMillan T_c .

Implementation III



Present Status

- Test bench: FCC aluminium
- Reproduce results from DECAFT (could use PWSCF...)
- All isotropic calculations are implemented (not functional though)
- Debugging/Testing phase


Present Status

- Symmetrization questions:
 - Phase gauge for phonon eigenvectors influences the values of phonon linewidths
 - Exploit symops to use irred qpts, perts, and kpts
- Start with no symmetries (all pert kpt qpt) and impose FCC symmetry after the fact; should this be necessary?


Present Status II

Al electronic Band structure 16^3 kpts


top: abinit bottom: decaft




Present Status III



Present Status IV



Present Status V



Conclusions

- Should be close to our goal...
- Isotropic constants can already be of use
- Extension beyond superconductivity to other applications?
- Insulating systems... vary “Fermi energy” and sound different parts of the el-phon coupling
- Anisotropic formalism